

Technical data sheet
Membrana mdm[®] Ventia Metal

Characteristic	Test method	Unit	Result	Tolerance	
				Min.	Max.
Length	EN 1848 -2	m	25	-0	+0,5
Width	EN 1848 -2	m	1,5	-0,005	+0,005
Straightness	EN 1848 -2	-	Pass	-	-
Mass per unit area	EN 1849 -2	g/m ²	400	-10	+20
Thickness	EN 1849 -2	mm	8 +0,7	-1	1
Reaction to fire	EN 11925-2	class	F	-	-
Resistance to water penetration	EN 1928 A	class	W1	-	-
Water vapour transmission Properties	EN ISO 12572 C	m	0,020	-0,005	+0,02
Resistance to penetration of air	EN 12114	m ³ /(m ² x h x 50 Pa)	Max 0,05	-	-
Tensile properties: Maximum tensile force	EN 12311-1	N/50mm	MD 350	-60	+60
			CD 210	-30	+60
Tensile properties: elongation	EN 12311-1	%	MD 60	-30	+30
			CD 65	-30	+40
Resistance to tearing (nail shank)	EN 12310-1	N	MD 140	-20	+50
			CD 160	-40	+50
Dimensional Stability	EN 1107-2	%	1	-	-
Stability at low temperature	EN 1109	°C	-30	-	-
Artificial ageing by long term exposure to the combination Of UV radiation and elevated Temperature and heat (80°C)	Elongation EN 13859-1 annex C	%	MD 40	-25	+25
			CD 45	-15	+15
	Tensile strength EN 13859-1 annex C	N/50mm	MD 270	-60	+60
			CD 180	-40	+40
Resistance to water penetration EN 13859-1 annex C	class	W1	-	-	
Water vapour transmission 23°C/85%RH	Lyssy	g/m ² x 24h	1500	-200	+200
Water vapour transmission 38°C/90%RH	Lyssy	g/m ² x 24h	3200	-400	+400

Bielsko-Biała, 30.03.2021
(Place and date of issue)

VAT No. PL5482614481
Registered in Poland, KRS No. 0000354101
Share capital: 992 500 PLN

Bank Handlowy w Warszawie S.A., SWIFT: CITIPLPX
IBAN: PL 67 1030 1508 0000 0008 1613 6008 (PLN)
IBAN: PL 23 1030 1508 0000 0008 1613 6024 (EUR)
IBAN: PL 98 1030 1508 0000 0008 1613 6032 (USD)